


FLEXO® WRAP

- Heavy Duty Hook And Loop Closure For Frequent Access
- Expands To Fit Over Inline Connectors And Splices
- Cut And Abrasion Resistant
- Halogen Free

Put-Ups

Nominal Size	Part #	Hook & Loop Width	Bulk Spool	Shop Spool	Available Colors	Lbs/ 100'
1/2"	FWN0.50	1/4"	100'	20'	4	1.30
3/4"	FWN0.75	5/8"	100'	15'	4	1.80
1 1/4"	FWN1.25	5/8"	100'	12'	4	2.30
2"	FWN2.00	5/8"	100'	10'	4	3.20
2 1/2"	FXN2.50BK	5/8"	100'	10'	BK	3.75




Cut Cleanly
Hot Knife

Flexible, Control & Management With Easy On, Easy Off Access

FLEXO WRAP (FW) is an exclusive product engineered and manufactured by Techflex. FW provides the perfect solution to a wide variety of unique application challenges.

The color matched hook and loop closure provides for easy on and off installation, as well as instant and convenient access for harness break-outs and rework of any specific section along the entire length of the run. Combined with the expandable, open weave design, FW will conform to a wide variety of bundle diameters and will wrap around irregular shapes.

- **Colors Available:**
4 = BK, WH, GY and BE.



- **The large overlap allows easy installation over splices and inline connectors without exposing wires and cables.**

Material
Polyethylene Terephthalate

Grade
FWN


Monofilament Diameter
.010"

Drawing Number
TF001FWPT-WD

Colors Available:



Black (BK), White (WH), Gray (GY) and Beige (BE).



FLEXO® WRAP



Abrasion Resistance
Medium

Abrasion Test Machine
Taber 5150

Abrasion Test Wheel
Calibrase H-18

Abrasion Test Load
500g

Room Temperature
70°F

Humidity
63%

Visible Hole Through
Material Destroyed
900 Test Cycles

Pre-Test Weight
3,772.7 mg

Post-Test Weight
3,391.1mg

Test End Loss Of Mass
Point Of Destruction
381.6 mg



Rating _____ **UL94VO**



Chemical Resistance


1=No Effect 4=More Affected
 2=Little Effect 5=Severely Affected
 3=Affected

Aromatic Solvents _____	2
Aliphatic Solvents _____	1
Chlorinated Solvents _____	3
Weak Bases _____	1
Salts _____	1
Strong Bases _____	2
Salt Water 0-S-1926 _____	1
Hydraulic Fluid MIL-H-5606 _____	1
Lube Oil MIL-L-7808 _____	1
De-Icing Fluid MIL-A-8243 _____	1
Strong Acids _____	3
Strong Oxidants _____	2
Esters/Keytones _____	1
UV Light _____	1
Petroleum _____	1
Fungus ASTM G-21 _____	1
Halogen Free _____	Yes
RoHS _____	Yes
SVHC _____	None

Melt Point
 ASTM D-2117
482°F (250°C)

Maximum Continuous
 Mil-I-23053
257°F (125°C)

Minimum Continuous
-103°F (-75°C)



PHYSICAL PROPERTIES

Monofilament Diameter _____	.010
ASTM D-204	
Flammability Rating _____	UL94
Recommended Cutting _____	Hot Knife
Colors _____	4
Wall Thickness _____	.025
Tensile Strength (Yarn) _____	7.5
ASTM D-2256 Lbs	
Specific Gravity ASTM D-792 _____	1.38
Moisture Absorption _____	1-.2
% ASTM D-570	
Hard Vacuum Data ASTM E-595	
TML _____	.19
CVCM _____	.00
WVR _____	.16
Smoke D-Max _____	56
ASTM E-662	
Outgassing _____	Med
Oxygen Index _____	21
ASTM D-2863	

www.techflex.com